

DESIGN AND DEVELOPMENT OF CONCRETE COVER BLOCK

Prof. S.A.Patage¹, More Poonam², Sonali pagire³, More Amit⁴, Gavate pooja⁵,

Prof S. A. Patage⁶

Civil Department, APCOER, Pune India

Abstract: Sufficient cover is required for the reinforcement in concrete structures for protection against corrosion. Though several codes of practices have specified minimum cover for various climatic conditions, it is often not maintained in practice. In this paper, the authors contend that the Indian Codal provisions relating to concrete cover have to be revised as they do not account for many factors related to minimum concrete cover. Also, some devices and methods to increase the quality of cover are discussed. The authors also stress that just an increase in concrete cover does not ensure durable structure.

I. INTRODUCTION

All The precast concrete product, which is used to provide the necessary covers or spacing for the reinforcement bars from the formwork, in all the RCC structures like slab, beam, column, footing, etc are called concrete cover blocks or concrete spacer blocks. In order to prevent corrosion of the rebar, it needs to be fully embedded in concrete. By code, it usually needs about 2-3 inches of coverage on all sites.

So, the cover block lifts the rebar up by about 2-3 inches & becomes a permeant and integral part of the poured concrete, ensuring that no part of the rebar sags and minimizes that required concrete coverage during the pour. They are available in variety of shapes and sizes as per their specific use.

II. PROBLEM STATEMENT

- Wherever Concrete cover does not have a structural function its purpose is to prevent damage occurring to the building part.
- It ensure that the concrete encase the steel on all sites so that it is not exposed to the external air.
- If the cover is insufficient the concrete can flake off, the steel is then no longer cover and may corrode.
- The building part is damage fundamentally in long term and this can lead failure.
- For the same depth of concrete section, the increase of concrete cover result in the reduction of the lever arm of internal resisting force.
- The weight of the concrete structure is increased the by an increases concrete cover.
- This effect is a critical factor in the design of floating ships and platforms where self-weight is an important design criterion.

III. OBJECTIVES

- The Maintain a specified distance between the rebars and the shuttering.
- To protect the steel reinforcement bars from environmental effects to prevent their corrosion.
- To provide thermal insulation, which protects the reinforcement bars from fire.
- Provide thermal insulation, which protects the reinforcement bars form the fire.
- Give reinforcing bars sufficient embedding to enable them to be stressed without slipping.
- To make a structure durable and safe.

IV. FUTURE SCOPE

- The The cover block can be manufacture with different shapes such as circular, cylindrical etc.

Cover blocks can be manufactured by replacing the existing constitutes with silica, sand, additives and different admixtures.

V. METHODOLOGY

- The For making M35 grade concrete Weight crush sand of 15kg in weighing machine.
- Take cement 5kg.
- Add 15ml admixture in 1ltr water and pour it in mixing.
- Take weight of water 2.25kg on weighing machine and add it in mixture.
- Mixed all material properly without any dryness.
- Take concrete cube mold of size 15 x 15 x 15 and cover blocks silicon mold.
- Apply oil on internal all side of silicon mold.
- Pour the concrete mixture in mold's up to top.
- Place the mold on vibrator machine and start the vibrating.
- Vibrate mould up to 12-15min.
- Leave the moulds for drying for 24hrs.
- Out the concrete block and cover blocks from the molds and place it in water for 7days.
- After 7days place concrete block for testing in CTM. We get the 7days result strength of m35 concrete.
- We get the 7days result strength of M35 concrete

RESULTS AND DISCUSSION

After the 7days we get the strength of M35 concrete in CTM 12.1N/mm²

[illegible]

- After the 28 days we get the strength of M35 concrete in CTM 29.0 N/mm^2

[illegible]

ACKNOWLEDGMENT

We have effort in this project; However, it would not have been possible without the Kind Support and help of many Individuals. We would like to extend our sincere thanks to all of them.

We would like to express out special thanks and gratitude to Principal of APCOER **Dr. S.B. Thakare** for giving us such attention and time.

We would like to express our special thanks and gratitude to Head of our Department **Prof. A. B. Shelar** for giving us such attention and time.

We are highly indebted to **Prof. S.A. Patage** for their guidance and constant supervision as well as for providing necessary information regarding the project & also for their Support in completion in the project.

We are also very thankful to **S.A.Patage** for co-ordinating and supporting us .

We would like to express our gratitude to words our parents and other staff of our collage for their kind co-operation and encouragement which helped us in completion of this project.

Our thanks and appreciation also go to people who have willingly helped us out with their abilities.

REFERENCES

1. Ali Seismic fragility curves for vulnerability assessment of steel fiber reinforced concrete segmental tunnel linings May 2018Tunnelling and Underground Space Technology78DOI:10.1016/j.tust.2018.04.032 Project:Seismic performance of steel fiber reinforced segmental lining Tunnels Authors: Mohammadn Jamshidi Avanaki University of Tehran Abdollah Hosseini University of Tehran Shahram Vahdani Cristian de Santos Albert De la Fuente Universitat Politècnica de Catalunya
2. Sustainability of Column-Supported RC Slabs: Fiber Reinforcement as an Alternative July 2019Journal of Construction Engineering and Management 145(7) DOI:10.1061/(ASCE)CO.1943-7862.0001667 Project: Decision making applied to project management and sustainability Authors: Albert De la Fuente Universitat Politècnica de Catalunya Maria del Mar Casanovas-Rubio Universitat Politècnica de Catalunya Oriol Pons Universitat Politècnica de Catalunya Jaume Armengou Universitat Internacional de Catalunya



3. Brian Adjetei Boye Jacobs engineering uk Samuel Partial Safety Factor for the Residual Flexural Strength of FRC Precast Concrete Segments
January 2018
DOI:10.1007/978-3-319-59471-2_203
In book: High Tech Concrete: Where Technology and Engineering Meet (pp.1768-1775)
Authors:
Albert De la Fuente
Universitat Politècnica de Catalunya
Víctor Cugat
4. Sergio Henrique Pia Changes in revological properties of mortar with steel slags and steel fiber by magnetic field.
DOI : July 2021.
Author : Dukman Kang
Doyoung Moon
5. Development of improved models for estimation of bursting stresses in elements under high concerntrated load
DOI : DEC 2018
Author : Samuel Jonah Abbey
Joao fonte
Samson Ngambi
6. Effects of hybrid steel fiber reinforced composit on structural performance of segmental linning subjected to TBM jacks
DOI : July 2019of
Author : Mohammad Jamshedi Avananki
7. Safety format for the flexural design of tunnel fiber reinforced concrete precast segmental lining.
DOI : SEPT 2020
Author : V. Cugat
Jesus Miguel bairan
Albert de la fuente
8. Development in design for fiber reinforced concrete tunnel segments
DOI : FEB. 2014
Author: Bakshi M.
Nasri V.
Iarissi Cavalaro
Loughborough University
Jesús Miguel Bairán
Universitat Politècnica de Catalunya